



Castin'Craft Clear Polyester Casting Resin

16 oz/473 mL, 32 oz/946 mL & 1 gallon/3.78 L

Technical Data Sheet

Castin'Craft Clear Polyester Casting Resin is promoted for ambient temperature cure with Castin'Craft Catalyst (MEK). It can be used to produce small, medium and large size castings with exceptional clarity. Castin'Craft Clear Polyester Casting Resin was designed to reduce cracks in larger castings with a long cure time, low peak exotherm, and minimal shrinkage.

TYPICAL RESIN PROPERTIES @ 77°F	RESULTS
Brookfield Viscosity. (RV) #2 @ 20 rpm	400 – 600
Catalyst %, DDM-9	1.0
Gel Time, min:sec	14:00 – 25:00
Gel to Peak Time, min:sec	35:00 – 60:00
Peak Exotherm °F (°C)	175–225 (79-107)
Solids %	62.0 – 64.5

MECHANICAL PROPERTIES OF NEAT CURED RESIN		RESULTS	
Property:	ASTM Test Method	Psi	Mpa
Flexural Strength	D-790	13,200	91
Flexural Modulus	D-790	7.32 x 10 ⁵	5048
Tensile Strength	D-638	6,400	44
Tensile Modulus	D-638	7.17 x 10 ⁵	4945
Tensile Elongation, %	D-638	1.5	1.5
Heat Distortion Temperature	D-648	115°F /	46.1°C
Hardness, Barcol 934-1	D-2583	38 -	42

All specifications and properties specified above are approximate. Specifications and properties of material may vary slightly from those given above. Environmental Technology Inc. makes no representations of fact regarding the material except those specified above. Final determination of the suitability of the material for the use contemplated is the sole responsibility of the buyer.

Revised: 3/2016



300 South Bay Depot Rd., Fields Landing, CA. 95537.

800-368-9323 707-443-9323 www.eti-usa.com mail@eti-usa.com